

Fabric Technical Data - Style 9948

Property		Value	Unit	Test method
Composition	Polyester	44	%	
	Woodpulp	56	%	
Basis weight		66	g/m ²	WSP 130.1
Thickness		0.38	mm	WSP 120.6
Absorbency		497	%	WSP 10.1
Extrinsic absorption capacity		337	ml/m ²	WSP 10.2
Grab tensile breaking strength (dry)	MD	154	N	ASTM D5034
	XD	68	N	
Strip tensile breaking strength (dry)	MD	181	N	WSP 110.4
	XD	46	N	

MD- LENGTHWISE, XD- CROSSWISE